

Sealing film

Contact us to find the right solution for your product



- Film performance has a huge impact on your product and your business
- We offer a one-stop shop solution to increase efficiency. You can buy trays and containers from Plus Pack and we will assist you in choosing the right sealing film
- We work with a variety of leading European film producers, therefore we can assist you with which film has exactly the properties that work best with your food, production process and packaging solution
- We offer onsite support when you start using a new film to help ensure a smooth production process

SEALING FILM		TRAY / CONTAINER						FEATURE					SEALING PROCESS				BARRIER			DETAILS			
Item no.	Item name	PET	PP	ALU PLAIN	ALU LACQ. PET	ALU LACQ. PP	Free from BPA	Micro-waveable film	Re-closable film	Gas flush	Anti fog	Max °C in food contact	Pre-heating	Sealing temperature To be tested!	Sealing pressure	Sealing time	Water vapor transmission	Oxygene transmission	Carbon dioxide	MOQ in square meter	MOQ in running meter	Diameter roll in mm	Meter roll
												°C/1h	°C/1h	°C	Bar	Sec.	g/m 2/24h	cm 3/m 2/24h	cm 3/m 2/24h	m 2	running meter	mm	m
22006509	FILM.WP.BIAXER.65µ.220MM.550M			X			X	X	X	X		90°C		160°C-200°C	Min.6	1,8-2,5	2	2	20	5.000	22.700	230	550
23006509	FILM.WP.BIAXER.65µ.230MM.550M			X			X	X	X	X		90°C		160°C-200°C	Min.6	1,8-2,5	2	2	20	5.000	21.700	230	550
26006509	FILM.WP.BIAXER.65µ.260MM.550M			X			X	X	X	X		90°C		160°C-200°C	Min.6	1,8-2,5	2	2	20	5.000	19.200	230	550
27506509	FILM.WP.BIAXER.65µ.275MM.1000M			X			X	X	X	X		90°C		160°C-200°C	Min.6	1,8-2,5	2	2	20	5.000	18.200	297	1000
28506509	FILM.WP.BIAXER.65µ.285MM.550M			X			X	X	X	X		90°C		160°C-200°C	Min.6	1,8-2,5	2	2	20	5.000	17.500	230	550
42006509	FILM.WP.BIAXER.65µ.420MM.550M			X			X	X	X	X		90°C		160°C-200°C	Min.6	1,8-2,5	2	2	20	5.000	11.900	230	550
28510000	FILM.SKINTITE.100µ.285MM.700M	X		X	X		X					85°C	100-130°C	180°C-210°C	4-5	1,8-2,5	5	2	9	4.788	16.800	314	700
16506201	FILM.TER.HB.50PET.EZP.165MM	X			X		X	X	X			95°C		120°C-140°C	4-5	0,5-1	8	3	13	7.480	44.000	310	1100
21506201	FILM.TER.HB.50PET.EZP.215MM	X			X		X	X	X			95°C		120°C-140°C	4-5	0,5-1	8	3	13	7.568	35.200	310	1100
23006201	FILM.TER.HB.50PET.EZP.230MM	X			X		X	X	X			95°C		120°C-140°C	4-5	0,5-1	8	3	13	7.568	35.200	310	1100
24006201	FILM.TER.HB.50PET.EZP.240MM	X			X		X	X	X			95°C		120°C-140°C	4-6	0,5-2	8	3	13	4.224	17.600	310	550